

KR9608119B1:

POLYPROPYLENE RESIN COMPOSITION

The resin composition comprises polyester resin and wood powder, suitable for molding fabrications such as injection molding or extrusion molding, the composition is prepared by the steps of: (A) per 100 parts by weight of wood powder surface-treated with a isocyanate system compound, mixing 15 to 70 parts by weight of denatured-polyolefin resin having a softening temperature of lower than 115 deg. C. with the wood powder at a temperature ranging from that of the above softening temperature of denatured-polypropylene resin to that of 120 deg. C.; (B) mixing and melting resultant compound with polypropylene resin.